PE Nr. 65-95, weiss-glänzend

Beschreibung
Coextrudierte PE-Folie geblasen, weiß glänzend, die Oberfläche ist mit Topcoat. Anwendbar als Dekor- und Informationsetiketten für Kosmetik, Lebensmittel, Chemieprodukte etc

Stärke:	95 µ	ISO 534

Klebstoff
Copolymere Acrylate, lösemittelfrei, hervorragende Licht- und Alterungsbeständigkeit, erfüllt die Spielzeugnorm EN 71/ Teil 3. Alle Klebstoffe sind für den Einsatz auf trockenen und feuchten, nicht fettenden Lebensmitteln geeignet (ISEGA Unbedenklichkeitserklärung).

Typ:	permanenten Acrylatkleber	
Stärke:	14 µ ± 6	
Schälfestigkeit:	25 N / mm	FTM 1 24h auf Glas

Min. Verarbeitungstemperatur: +5° C
Temperaturbeständigkeit - 30 bis + 90° C

Träger
Superkalandriertes, hochverdichtetes weißes Glassinepapier, hohe Reißfestigkeit, hervorragende Stanzeigenschaften, lösemittelfreie Silikonisierung

Flächengewicht	65 g/m²	ISO 536
Stärke:	57 µ	ISO 534

Bedruckbarkeit
Geeignet für konventionelle Bedruckungsarten: Buch-, Flexo-, UV-Offset-, Sieb- und Tiefdruck, alle auch mit UVTrocknung, sowie Heiß- und Kaltprägungen

Description
A thermal transfer printable polyester film with print receptive topcoat, high performance extra permanent acrylic adhesive and glassine liner.
This product has UL recognition (file MH 16635).

Caliper:	95 µ	ISO 534

Adhesive
Copolymer acrylate, solvent-free, outstanding resistance to light and aging, meets the toy standard EN71 /Part3. All adhesives are suitable for use on dry and moist, non-greasy foods (ISEGA declaration of non-objection).

Type:	*permanent acrylic adhesive*	
Coat weight:	*14 µ ± 6*	
Peel Adhesion:	25 N / mm	FTM 1

Min. Application temperature: +5 °C
Temperature resistance - 30 to + 90°C

Liner
Super-calendered, high-density white glassine paper, high tear resistance, excellent puncture properties, solvent-free siliconization

Caliper	*65 g/m²*	*ISO 536*
Thickness:	57 µ	ISO 534

Printability
Suitable for conventional types of printing: book, flexo, UV offset, screen and gravure printing, all also with UV drying, as well as hot and cold embossing

Haltbarkeit: 12 Monate, wenn die Weiterverarbeitung unter folgenden Lagerungsbedingungen unterzogen wurde, gilt: Dieses Material muß bei einer Temperatur von 22 ° C + 2 ° C und 50 + 5% relativer Feuchtigkeit gelagert werden. Der Lagerbereich muss trocken und sauber sein. Halten Sie das Material in der Originalverpackung, um es vor Staub und Verschmutzung zu schützen. Nicht der direkten Sonneneinstrahlung oder Wärmequellen aussetzen.

Die vorstehenden Angaben stellen unsere gegenwärtigen Erfahrungswerte dar. Es obliegt dem Besteller, vor Verwendung des Produktes selbst zu prüfen, ob es sich, auch im Hinblick auf mögliche anwendungswirksame Einflüsse, für den von ihm vorgesehenen Verwendungszweck eignet. Alle Fragen einer Gewährleistung und Haftung, einschließlich der Gewährleistungsfrist für dieses Produkt, regeln sich nach unseren jeweils gültigen Allgemeinen Verkaufsbedingungen, sofern nicht gesetzliche Vorschriften etwas anderes vorsehen. Keine Gewährleistung und Haftung übernimmt die MARSCHALL GmbH & Co. KG für die Verarbeitung der Folien.

***Shelf life**: 12 months, applicable only to the material delivered which has not undergone further processing, under the following storage conditions: this material must be stored at a temperature of 22°C + 2°C and 50 + 5% of Relative Humidity. Storage area must be dry and clean. Keep the material in the original packaging when not used in order to protect it from dust and contamination. Do not expose to direct sunlight or heat sources.*

The data represents our present empirical values . It is up to the purchaser, before using the product to check for yourself if it is, also in a view of possible application related influences, is suitable for the intended use of it. All questions of warranty and liability, including the warranty period for this product are governed by our currently valid General Conditions, unless legal regulations provide somewhat different. No warranty or liability takes MARSCHALL GmbH & Co. KG for the processing of the films.

issue date: April-2015

MARSCHALL GmbH & Co. KG
Etiketten + Drucksysteme

Hebbelstr. 2-4
D-32457 Porta Westfalica
fon +49(0)5731.7644-00
fax +49(0)5731.7644-11

info@marschall-pw.de
www.marschall-pw.de